

Intended use

Mipa PUR HS 2K-Acryl-HS Fahrzeuglack is a weather- and yellowing- resistant High-Solid car paint for VOC-compliant partial or complete paintworks on trucks, busses and commercial vehicles. It provides particularly high opacity, spreading rate, gloss retention and resistance to chemical and mechanical strain.


Spreading rate: 10,0 - 14,0 m²/l

Processing instructions



Colour

Mipa Mix-System



Mixing ratio

Hardener

Mipa 2K-HS-Härter

Mipa 2K-MS-Härter

by weight (lacquer : hardener)

--

--

by volume (lacquer : hardener)

3 : 1

2 : 1



Hardener

for complete paintwork

Mipa 2K-HS-Härter HS 25 / 35

Mipa 2K-MS-Härter MS 25 / 40

for partial paintwork

Mipa 2K-HS-Härter HS 10

Mipa 2K-Härter MS 10



Pot life

1 h with Mipa 2K-Härter HS 10, MS 10 at 20 °C

2 h with Mipa 2K-Härter HS 25, MS 25 at 20 °C

4 h with Mipa 2K-Härter HS 35, MS 40 at 20 °C



Thinner

Mipa 2K-Verdünnung kurz V 10

Mipa 2K-Verdünnung V 25

Mipa 2K-Verdünnung lang V 40



Spray viscosity

Thin only when using Mipa HS-Härter (hardener). There is no need to thin when using Mipa MS-Härter (hardener).

gravity spray gun

25 - 30 e 1 mm DIN

Airmix/Airless

25 - 30 e 1 mm DIN



Application mode

Application mode

Gravity spray gun (high pressure)

HVLP (low pressure)

HVLP / internal nozzle pressure

Airmix / Airless

Hardener

--

--

--

--

pressure (bar)

2 - 2,5

2 - 2,2

0,7

100 - 120

nozzle (mm)

1,2 - 1,3

1,2 - 1,3

--

0,23 - 0,28

spray passes

1 - 2

1 - 2

--

1


Thinner

5 - 10

5 - 10

--

5 - 10



Flash-off time

5 - 8 min between coats

10 - 15 min before oven drying

Dry coat thickness

50 - 60 µm



Drying time

object temperature	dust dry	set to touch	ready for assembly	sandable	recoatable
20 °C	45 - 55 min	5 - 6 h	12 - 24 h	--	--
60 °C	10 - 15 min	25 - 30 min	after cooling	--	--
Infrared drying shortwave	--	8 min	--	--	--
Infrared drying mediumwave	--	10 - 15 min	--	--	--

Note

Storage: at least 3 years in unopened original container

VOC Regulation : EU limit value for this product (category B/d): 420 g/l
This product contains max. 420 g/l of VOC.

Processing conditions: From +10 °C and up to 80 % relative air humidity. Ensure an adequate supply and exhaust air ventilation.

Processing instructions: To avoid too thick layers (very high solids content as HS quality) strictly observe the recommended number of coats. Check colours before application. Always check colours after having added the hardener. The polishability of some colours may be limited due to the system. For subsequently matting with Mipa Multi Mat please observe the mixing ratios and information about application mentioned in the technical data sheet of Mipa Multi Mat.